

BRADYBONDZ™ B-8425 GLOSS POLYPROPYLENE THERMAL TRANSFER PRINTABLE LABELSTOCK

TDS No. B-8425
Effective Date: 02/04/2019

Description:

GENERAL

Print Technology: Thermal Transfer

Material Type: Polypropylene

Finish: Gloss

Adhesive: Permanent Acrylic

APPLICATIONS

B-8425 is designed for general purpose label, asset identification, rating plate, and warning/instructional labeling.

RECOMMENDED RIBBONS

Brady Series R6000 Halogen Free black thermal transfer ribbon

Brady Series R4400 colored thermal transfer ribbons.

REGULATORY/AGENCY APPROVALS

UL: B-8425 is a UL Recognized Component to UL969 Labeling and Marking Standard when printed with the Brady Series R6000 ribbon. See UL file MH17154 for specific details. UL information can be accessed online at UL.com in the UL Product iQ area.

CSA: B-8425 is CSA Accepted to C22.2 No.0.15-95 Adhesive Labels Standard when printed with the Brady Series R6000 ribbon. B-8425 is approved to Type A. See CSA file 041833 for specific details. CSA information can be accessed online at directories.csa-international.org.

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total (excluding liner)	0.0023 inch (0.0584 mm) 0.0008 inch (0.0203 mm) 0.0031 inch (0.0787 mm)
Adhesion to:	ASTM D 1000	
-Stainless Steel	20 minute dwell 24 hour dwell	35 oz/inch (38 N/100 mm) 41 oz/inch (44 N/100 mm)
-Smooth ABS	20 minute dwell 24 hour dwell	33 oz/inch (35 N/100 mm) 35 oz/inch (38 N/100 mm)
-Polypropylene	20 minute dwell 24 hour dwell	23 oz/inch (26 N/100 mm) 28 oz/inch (31 N/100 mm)
-Glass	20 minute dwell 24 hour dwell	34 oz/inch (38 N/100 mm) 37 oz/inch (40 N/100 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack (0.5 second dwell, 1 cm/sec separation)	22.9 oz (646 g)
Tensile Strength and Percent Elongation at Break	ASTM D 1000 -Machine -Cross Direction	48 lbs/inch (841 N/100 mm), 35% 41 lbs/inch (718 N/100 mm), 47%

Performance properties were tested using B-8425 printed with the Brady Series R6000 Halogen Free ribbon. Printed samples of B-8425 were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environmental conditions.

PERFORMANCE PROPERTIES	TEST METHOD	TYPICAL RESULTS
Long Term High Service Temperature	30 days at 194°F (90°C)	No visible effect to label at 90°C
Low Service Temperature	30 days at -40°F (-40°C) 30 days at -94°F (-70°C)	No visible effect
Humidity Resistance	30 days at 100°F (37°C) and 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	No visible effect
Weatherability ¹	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	Moderate cracking of label stock. Label is still legible.
Abrasion Resistance	Taber Abraser, CS-10 grinding wheels, 250 g/arm (Fed. Std. 191A, Method 5306)	Print legible to: R6000: 100 cycles

¹B-8425 is not recommended for long-term outdoor use.

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
----------------------	---------------------

Samples were printed with the Brady Series R6000 Halogen Free ribbon. Samples laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Test was conducted at room temperature except where noted. Testing consisted of 5 cycles of 10 minute immersions in the specified test fluid followed by a 30 minute recovery period. After final immersion, samples rubbed 10 times with cotton swab saturated with test fluid.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE	
	LABEL STOCK SUBSTRATE/ADHESIVE	R6000 Halogen Free
Methyl Ethyl Ketone	No visible effect	No visible effect without rub, complete print removal after rub
Isopropyl Alcohol	No visible effect	No visible effect without rub, severe print removal after rub
Mineral Spirits	No visible effect	No visible effect without rub, slight print fade with rub
SAE 20 WT Oil	No visible effect	No visible effect with and without rub
Formula 409®	No visible effect	No visible effect without rub, severe print removal with rub
3% Alconox® Detergent	No visible effect	No visible effect without rub, moderate print fade with rub
10% Sodium Hydroxide Solution	No visible effect	No visible effect with and without rub
10% Sulfuric Acid Solution	No visible effect	No visible effect with and without rub

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

Alconox® is a registered trademark of Alconox Co.

Formula 409® is a registered trademark of the Clorox Company

Polyken™ is a trademark of Testing Machines Inc.

Sunlighter™ is a trademark of the Test Lab Apparatus Company

ASTM: American Society for Testing and Materials (U.S.A.)

SAE: Society of Automotive Engineers (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289